

COMPANY WITH MANAGEMENT SYSTEM - UNI EN ISO 9001 -- UNI EN ISO 14001 -

Sherwin-Williams Italy S.r.l. – con unico socio Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18 tel. +39 051 770 511 - fax +39 051 777 437 www.sayerlack.com Cod. Fisc. e Reg. Impr. Bo 08866930152 P. IVA: IT 00494251200 - R.E.A. n. 313180 Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

Техническая карта

IF0501/00 SAYERGUM

Заменяет предыдущую версию от 12/06/06

ДАТА 07/15/13

Цвета:	Прозрачный
Область применения:	Кухонные фасады, мебель
Метод нанесения:	Распыление
Процедура смешивания:	по весу (кг.) по объёму (л.)
Часть А:	IF0501/00 100 100
Часть В (отвердитель):	TH2520/00 30 30
Разбавитель:	DT1150/00 40-60 40-60

Подготовка поверхности:

Цветными эмалями TZ88**/XX - TZ99**/XX. Для достижения необходимого эффекта рекомендуется нанесение в 1 слой.

Технические характеристики:

Сухой остаток (%):	31 ± 2
Вязкость (DIN 4 при 20°C):	20

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.



COMPANY WITH
MANAGEMENT SYSTEM
- UNI EN ISO 9001 - UNI EN ISO 14001 -

Sherwin-Williams Italy S.r.l. – con unico socio Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18 tel. +39 051 770 511 - fax +39 051 777 437 www.sayerlack.com Cod. Fisc. e Reg. Impr. Bo 08866930152 P. IVA: IT 00494251200 - R.E.A. n. 313180 Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

Общие характеристики:

Расход (гр/м²):	80÷120
Время сушки (100 гр/м² при 20°C)	пылестойкость: 20-30 мин. на отлип: 6-8 часов полное высыхание: 48 часов
Срок хранения:	При соблюдении правил хранения продукта, срок хранения не ограничен.
	После долгих периодов хранения продукта всегда проверяйте его однородность и тщательно вымешивайте во избежание образования осадка.

IF0501/00 SAYERGUM - "бархатистый" спецэффект, немного резиновый на ощупь, высокостойкий к царапинам. Отличная прозрачность даже на тёмных подложках.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.